


## PROMINA® 60

Calcium silicate fire resistant board



### Product description

PROMINA® 60 is a non combustible matrix engineered mineral board reinforced with selected fibres and fillers. It does not contain formaldehyde or any asbestos. The product is dimensionally stable and resistant to the effects of moisture. Its performance characteristics are not degraded by moisture. PROMINA®60 is suitable for internal use in high humidity conditions and external semi-exposed use. For fully exposed conditions, consult Promat Technical Department.

### Benefits

- Non-combustible
- Stable board characteristic at high temperature
- Resistant to effects of moisture and humidity
- Specifically tested and proven on its fire performance in BS standards and designated system applications
- Up to 2 hours fire rating for selected system application
- Slim construction by using this board to achieve the desired fire rating

### Fire Resistant Applications

- Internal drywalls
- Internal lining to external walls
- Suspended and self-supporting hanger free ceilings
- Cladding to steel sheet metal ducts
- Enclosures to Pipes & services
- Smoke screens

Material properties	
General description	Calcium Silicate Board Engineered with Mineral Matrix Structure (Promaxon® technology)
Surface condition & appearance	Light grey colour Front face: smooth Back face: sanded
Nominal dry density (average)	Approx. 1000kg/m <sup>3</sup>
Moisture Content	Approx. 6.0% The moisture content varies and will reach an equilibrium over time with the atmospheric relative humidity of the environment
Alkalinity	Approx. pH 12
Thickness tolerance	Compliant with thickness tolerance of CE requirements (9mm thick standard sheets, +/-0.5mm)
Dimension tolerance	±5mm (standard board dimensions)

Static Values			
Modulus of Elasticity E	Flexural Strength F	Tensile strength T	Compressive strength $\perp$
Longitudinal: 4.1kN/mm <sup>2</sup> Transverse: 4.1kN/mm <sup>2</sup>	Longitudinal: 10.0N/mm <sup>2</sup> Transverse: 7.0N/mm <sup>2</sup>	Longitudinal: 4.1N/mm <sup>2</sup> Transverse: 2.1N/mm <sup>2</sup>	7.76N/mm <sup>2</sup>

Reaction to Fire & Thermal Properties		
Combustibility	Surface burning	Thermal conductivity
A1 Classification: EN 13501-1 Non-combustible: BS 476: Part 4	Class 0: BS 476: Part 6 & 7	0.136W/m <sup>2</sup> K

# PROMINA® 60

## Calcium silicate fire resistant board

Standard thickness	Standard dimension	Number of boards per pallet	Surface area per pallet	Weight of standard sheet	Weight per pallet
9mm	2440mm x 1220mm	61	181.5m <sup>2</sup>	Approx. 30kg	Approx. 1970kg
12mm	2440mm x 1220mm	46	136.9 m <sup>2</sup>	Approx. 40kg	Approx. 1981kg
15mm	2440mm x 1220mm	36	107.2 m <sup>2</sup>	Approx. 50kg	Approx. 1941kg

All physical and mechanical values are averages based on standard production and tested according to internal procedures. The typical values are given for guidance. The figures can change dependent on the test methods used. If a particular value is of prime importance for a specification, please consult Promat Technical Department.

## Manufacturing Certification

PROMINA® 60 is manufactured under a quality management system certified in accordance with ISO 9001:2015. The manufacturing site is also certified to meet the environmental standards of ISO 14001: 2015 and the occupational health & safety requirements of ISO 45001:2018.

### Australia

#### Promat Australia Pty Ltd

##### South Australia office

1 Scotland Road  
SA 5031 Mile End South  
☎ 1800 Promat (776 628)  
✆ +61 8 8352 1014  
✉ PAPT.mail@etexgroup.com

##### New South Wales office

Unit 1, 175 Briens Road  
Northmead, NSW 2152  
☎ 1800 Promat (776 628)  
✆ +61 2 9630 0258  
✉ PAPT.mail@etexgroup.com

##### Victoria office

Unit 1, 355 Grieve Parade  
Altona North, VIC 3025  
☎ 1800 Promat (776 628)  
✆ 1800 334 598  
✉ PAPT.mail@etexgroup.com

##### Queensland office

80 Stradbroke St  
Heathwood QLD 4110  
☎ 1800 011 376  
✆ 1800 334 598  
✉ PAPT.mail@etexgroup.com

### China

#### Promat Shanghai Ltd

No.2, Tai Hua Street  
Yonghe Economic District  
Guangzhou City  
Guangdong Province 511356  
☎ +86 20 8136 1167  
✉ promat.cn@etexgroup.com

### Hong Kong

#### Promat International (Asia Pacific) Ltd

Room 1010, C.C. Wu Building  
302-308 Hennessy Road  
Wanchai  
☎ +852 2836 3692  
✉ promat.hk@etexgroup.com

### Malaysia

#### Etex Malaysia Sdn Bhd

Unit 19-02-01, Level 2, Wisma Tune  
19 Lorong Dungun, Damansara Heights  
50490 Kuala Lumpur  
☎ +60 3 2095 8555  
✉ promat.my@etexgroup.com

### Singapore

#### Promat Building System Pte Ltd

10 Science Park Road, #03-02 The Alpha  
Singapore Science Park II  
117684 Singapore  
☎ +65 6776 7635  
✉ promat.sg@etexgroup.com

- The technical data provided in this publication is based on mean values prevalent at time of publication and is thus subject to fluctuation. It should not be regarded as a guarantee to system performance.
- All data contained herein conforms to and frequently surpasses generally accepted fire protection standards recognised by most professional fire science practitioners and regulatory authorities worldwide. The same general principle is equally applicable to all Promat products and systems. Promat has access to a considerable body of test authentication data and this can be provided on a complimentary basis upon request. It should be noted however that this publication replaces all previous editions in its entirety.
- This document is protected by International copyright laws. Reproduction and distribution in whole or in part without prior written permission is strictly prohibited. PROMAT, PROMINA and logo are registered trademark of Etex NV or an affiliate thereof in Asia Pacific and/or other countries. Any use without authorisation is prohibited and may violate trademark laws.



[www.promat.com](http://www.promat.com)



Promat Asia Pacific